

# Overland Range Technical Data Sheet

# BRICKWORKS

Product Range	Product Name	Dimension Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Units per Square Metre	Pack Size	Characteristic Unconfined Compressive Strength (f <sub>uc</sub> ) MPa	Maximum Cold Water Absorption (%)	Initial Rate of Absorption (IRA) (kg/m <sup>2</sup> min)	Coefficient of Expansion Factor (mm/m)	Durability Class	Liability to Efflorescence	Lime Pitting Liability	LRV
Overland	Cradle Pristine			CQLD	230	110	76	DW1	48.5	384	>12	12	0.5-2.5	1.0	Exposure Grade	Slight	Slight	13
Overland	Freycinet Pristine			CQLD	230	110	76	DW1	48.5	384	>12	12	0.5-2.5	1.0	Exposure Grade	Slight	Slight	12.2
Overland	Huon Pristine			CQLD	230	110	76	DW1	48.5	384	>12	12	0.5-2.5	1.2	General Purpose	Slight	Slight	19.7
Overland	Tarkine Pristine			CQLD	230	110	76	DW1	48.5	384	>12	12	0.5-2.5	1.2	General Purpose	Slight	Slight	26.5
Overland	Bruny Pristine			CQLD	230	110	76	DW1	48.5	384	>12	12	0.5-2.5	1.0	General Purpose	Slight	Slight	
Overland	Flinders Pristine			CQLD	230	110	76	DW1	48.5	384	>12	12	0.5-2.5	1.0	General Purpose	Slight	Slight	20.8
Overland	Tasman Blend Blended			CQLD	230	110	76	DW1	48.5	384	>12	12	0.5-2.5	1.0	General Purpose	Slight	Slight	19.2
Overland	Cradle Rugged			CQLD	230	110	76	DW1	48.5	384	>12	12	0.5-2.5	1.0	Exposure Grade	Slight	Slight	14.5
Overland	Franklin Gordon Blend Blended			CQLD	230	110	76	DW1	48.5	384	>12	12	0.5-2.5	1.0	Exposure Grade	Slight	Slight	7.7
Overland	Freycinet Rugged			CQLD	230	110	76	DW1	48.5	384	>12	12	0.5-2.5	1.0	Exposure Grade	Slight	Slight	14.6
Overland	Huon Rugged			CQLD	230	110	76	DW1	48.5	384	>12	12	0.5-2.5	1.2	General Purpose	Slight	Slight	24.7
Overland	Tarkine Rugged			CQLD	230	110	76	DW1	48.5	384	>12	12	0.5-2.5	1.2	General Purpose	Slight	Slight	26.2
Overland	Bruny Rugged			CQLD	230	110	76	DW1	48.5	384	12	12	0.5-2.5	1.0	General Purpose	Slight	Slight	

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.

