




























Overland Range Technical Data Sheet

BRICKWORKS

Product Range	Product Name	Dimension Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight / Unit (kg)	Core Volume (%)	Units per Square Metre	Pack Size	Characteristic Unconfined Compressive Strength (f _{uc}) MPa	Maximum Cold Water Absorption (%)	Initial Rate of Absorption (IRA) (kg/m ² min)	Coefficient of Expansion Factor (mm/m)	Durability Class	Liability to Efflorescence	Lime Pitting Liability	LRV
Overland	Bruny Rugged			TAS	230	110	76	DW1	3.2	<25	48.5	384	<12	<12	0.5-2.5	<1.0	General Purpose	Slight	Slight	
Overland	Flinders Rugged			TAS	230	110	76	DW1	3.2	<25	48.5	384	>12	<12	0.5-2.5	<1.0	General Purpose	Slight	Slight	22.2
Overland	Huon Pristine			TAS	230	110	76	DW1	3.2	<25	48.5	384	>12	<12	0.5-2.5	<1.2	General Purpose	Slight	Slight	19.7
Overland	Bruny Pristine			TAS	230	110	76	DW1	3.2	<25	48.5	384	>12	<12	0.5-2.5	<1.0	General Purpose	Slight	Slight	
Overland	Flinders Pristine			TAS	230	110	76	DW1	3.2	<25	48.5	384	>12	<12	0.5-2.5	<1.0	General Purpose	Slight	Slight	20.8
Overland	Cradle Pristine			TAS	230	110	76	DW1	3.2	<25	48.5	384	>12	<12	0.5-2.5	<1.0	Exposure Grade	Slight	Slight	13
Overland	Huon Rugged			TAS	230	110	76	DW1	3.2	<25	48.5	384	>12	<12	0.5-2.5	<1.2	General Purpose	Slight	Slight	24.7
Overland	Tarkine Rugged			TAS	230	110	76	DW1	3.2	<25	48.5	384	>12	<12	0.5-2.5	<1.2	General Purpose	Slight	Slight	26.2
Overland	Freycinet Pristine			TAS	230	110	76	DW1	3.2	<25	48.5	384	>12	<12	0.5-2.5	<1.0	Exposure Grade	Slight	Slight	12.2
Overland	Tasman Blend Blended			TAS	230	110	76	DW1	3.2	<25	48.5	384	>12	<12	0.5-2.5	<1.0	General Purpose	Slight	Slight	19.2
Overland	Freycinet Rugged			TAS	230	110	76	DW1	3.2	<25	48.5	384	>12	<12	0.5-2.5	<1.0	Exposure Grade	Slight	Slight	14.6
Overland	Franklin Gordon Blend Blended			TAS	230	110	76	DW1	3.2	<25	48.5	384	>12	<12	0.5-2.5	<1.0	Exposure Grade	Slight	Slight	7.7
Overland	Tarkine Pristine			TAS	230	110	76	DW1	3.2	<25	48.5	384	>12	<12	0.5-2.5	<1.2	General Purpose	Slight	Slight	26.5
Overland	Cradle Rugged			TAS	230	110	76	DW1	3.2	<25	48.5	384	>12	<12	0.5-2.5	<1.0	Exposure Grade	Slight	Slight	14.5

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.

Please note: FRL applies up to 3m high - restrained on top and bottom.

