


Overland Range Technical Data Sheet

BRICKWORKS

| Product Range | Product Name                  | Dimension Illustration                                                              | Swatch                                                                              | State | Length (mm) | Width (mm) | Height (mm) | Dimensional Category | Units per Square Metre | Pack Size | Characteristic Unconfined Compressive Strength (f'uc) MPa | Maximum Cold Water Absorption (%) | Initial Rate of Absorption (IRA) (kg/m2 min) | Coefficient of Expansion e Factor (mm/m) | Durability Class | Liability to Efflorescence | Lime Pitting Liability | LRV  |
|---------------|-------------------------------|-------------------------------------------------------------------------------------|-------------------------------------------------------------------------------------|-------|-------------|------------|-------------|----------------------|------------------------|-----------|-----------------------------------------------------------|-----------------------------------|----------------------------------------------|------------------------------------------|------------------|----------------------------|------------------------|------|
| Overland      | Cradle Pristine               |    |    | VIC   | 230         | 110        | 76          | DW1                  | 48.5                   | 384       | >12                                                       | 12                                | 0.5-2.5                                      | 1.0                                      | Exposure Grade   | Slight                     | Slight                 | 13   |
| Overland      | Freycinet Pristine            |    |    | VIC   | 230         | 110        | 76          | DW1                  | 48.5                   | 384       | >12                                                       | 12                                | 0.5-2.5                                      | 1.0                                      | Exposure Grade   | Slight                     | Slight                 | 12.2 |
| Overland      | Huon Pristine                 |    |    | VIC   | 230         | 110        | 76          | DW1                  | 48.5                   | 384       | >12                                                       | 12                                | 0.5-2.5                                      | 1.2                                      | General Purpose  | Slight                     | Slight                 | 19.7 |
| Overland      | Tarkine Pristine              |    |    | VIC   | 230         | 110        | 76          | DW1                  | 48.5                   | 384       | >12                                                       | 12                                | 0.5-2.5                                      | 1.2                                      | General Purpose  | Slight                     | Slight                 | 26.5 |
| Overland      | Bruny Pristine                |    |    | VIC   | 230         | 110        | 76          | DW1                  | 48.5                   | 384       | >12                                                       | 12                                | 0.5-2.5                                      | 1.0                                      | General Purpose  | Slight                     | Slight                 |      |
| Overland      | Flinders Pristine             |    |    | VIC   | 230         | 110        | 76          | DW1                  | 48.5                   | 384       | >12                                                       | 12                                | 0.5-2.5                                      | 1.0                                      | General Purpose  | Slight                     | Slight                 | 20.8 |
| Overland      | Flinders Rugged               |                                                                                     |    | VIC   | 230         | 110        | 76          | DW1                  | 48.5                   | 384       | >12                                                       | 12                                | 0.5-2.5                                      | 1.0                                      | General Purpose  | Slight                     | Slight                 | 22.2 |
| Overland      | Tasman Blend Blended          |    |    | VIC   | 230         | 110        | 76          | DW1                  | 48.5                   | 384       | >12                                                       | 12                                | 0.5-2.5                                      | 1.0                                      | General Purpose  | Slight                     | Slight                 | 19.2 |
| Overland      | Cradle Rugged                 |    |    | VIC   | 230         | 110        | 76          | DW1                  | 48.5                   | 384       | >12                                                       | 12                                | 0.5-2.5                                      | 1.0                                      | Exposure Grade   | Slight                     | Slight                 | 14.5 |
| Overland      | Franklin Gordon Blend Blended |    |    | VIC   | 230         | 110        | 76          | DW1                  | 48.5                   | 384       | >12                                                       | 12                                | 0.5-2.5                                      | 1.0                                      | Exposure Grade   | Slight                     | Slight                 | 7.7  |
| Overland      | Freycinet Rugged              |    |    | VIC   | 230         | 110        | 76          | DW1                  | 48.5                   | 384       | >12                                                       | 12                                | 0.5-2.5                                      | 1.0                                      | Exposure Grade   | Slight                     | Slight                 | 14.6 |
| Overland      | Huon Rugged                   |    |   | VIC   | 230         | 110        | 76          | DW1                  | 48.5                   | 384       | >12                                                       | 12                                | 0.5-2.5                                      | 1.2                                      | General Purpose  | Slight                     | Slight                 | 24.7 |
| Overland      | Tarkine Rugged                |  |  | VIC   | 230         | 110        | 76          | DW1                  | 48.5                   | 384       | >12                                                       | 12                                | 0.5-2.5                                      | 1.2                                      | General Purpose  | Slight                     | Slight                 | 26.2 |
| Overland      | Bruny Rugged                  |  |  | VIC   | 230         | 110        | 76          | DW1                  | 48.5                   | 384       | 12                                                        | 12                                | 0.5-2.5                                      | 1.0                                      | General Purpose  | Slight                     | Slight                 |      |

This Data represents average results from commercial production lots.  
If specific test results are required, sample should be taken from current production lots.  
AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.

